



# Standard Specification for Wrought Titanium-6Aluminum-4Vanadium ELI (Extra Low Interstitial) Alloy for Surgical Implant Applications (UNS R56401)<sup>1</sup>

This standard is issued under the fixed designation F 136; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope \*

1.1 This specification covers the chemical, mechanical, and metallurgical requirements for wrought annealed titanium-6aluminum-4vanadium ELI (extra low interstitial) alloy (R56401) to be used in the manufacture of surgical implants.

1.2 The values stated in inch-pound units are to be regarded as the standard. The SI equivalents in parentheses are provided for information only.

## 2. Referenced Documents

### 2.1 ASTM Standards:

E 8 Test Methods of Tension Testing of Metallic Materials<sup>2</sup>

E 120 Test Methods for Chemical Analysis of Titanium and Titanium Alloys<sup>3</sup>

E 290 Test Method for Bend Testing of Materials for Ductility<sup>3</sup>

E 527 Practice for Numbering Metals and Alloys (UNS)<sup>4</sup>

E 1409 Test Method for Determination of Oxygen in Titanium and Titanium Alloys by the Inert Gas Fusion Technique<sup>5</sup>

E 1447 Test Method for Determination of Hydrogen in Titanium and Titanium Alloys by the Inert Gas Fusion Thermal Conductivity Method<sup>3</sup>

F 981 Practice for Assessment of Compatibility of Biomaterials for Surgical Implants with Respect to Effect of Materials on Muscle and Bone<sup>6</sup>

### 2.2 ASQ Standard:

ASQ C1 Specifications of General Requirements for a Quality Control Program<sup>7</sup>

### 2.3 Aerospace Material Specifications:<sup>8</sup>

AMS 2249 Chemical Check Analysis Limits, Titanium and Titanium Alloys

AMS 4930 Titanium Alloy Bars, Forgings, and Rings 6AL-4V Extra Low Interstitial Annealed

### 2.4 Society of Automotive Engineers Standard:

SAE J1086 Practice for Numbering Metals and Alloys (UNS)<sup>9</sup>

## 3. Terminology

### 3.1 Definitions of Terms Specific to This Standard:

3.1.1 *lot, n*—the total number of mill products produced from one heat under the same conditions at essentially the same time.

## 4. Product Classification

4.1 *Strip*—Any product under 0.1875 in. (4.75 mm) in thickness and under 24 in. (610 mm) wide.

4.2 *Sheet*—Any product under 0.1875 in. (4.75 mm) in thickness and 24 in. (610 mm) or more in width.

4.3 *Plate*—Any product 0.1875 in. (4.75 mm) thick and over and 10 in. (254 mm) wide and over, with widths greater than five times thickness. Plate up to 4.00 in. (101.60 mm), thick inclusive is covered by this specification.

4.4 *Bar*—Round bars and flats from 0.1875 in. (4.75 mm) to 4.00 in. (101.60 mm) in diameter or thickness (other sizes and shapes by special order).

4.5 *Forging Bar*—Bar as described in 4.4, used for production of forgings, may be furnished in the hot rolled condition.

4.6 *Wire*—Rounds less than 0.1875 in. (4.75 mm) in diameter.

## 5. Ordering Information

5.1 Include with inquiries and orders for material under this specification the following information:

5.1.1 Quantity,

5.1.2 ASTM designation and date of issue,

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee F04 on Medical and Surgical Materials and Devices and is the direct responsibility of Subcommittee F04.12 on Metallurgical Materials.

Current edition approved Nov. 10, 2002. Published December 2002. Originally published in 1984. Last previous edition approved in 2002 as F 136 – 02.

<sup>2</sup> *Annual Book of ASTM Standards*, Vol 03.01.

<sup>3</sup> *Annual Book of ASTM Standards*, Vol 03.05.

<sup>4</sup> *Annual Book of ASTM Standards*, Vol 01.01.

<sup>5</sup> *Annual Book of ASTM Standards*, Vol 03.06.

<sup>6</sup> *Annual Book of ASTM Standards*, Vol 13.01.

<sup>7</sup> Available from American Society for Quality, 600 N. Plankinton Ave., Milwaukee, WI 53203.

<sup>8</sup> Available from Society of Automotive Engineers (SAE), 400 Commonwealth Dr., Warrendale, PA 15096-0001.

<sup>9</sup> New designation established in accordance with E 527 and SAE J1086.

\*A Summary of Changes section appears at the end of this standard.

- 5.1.3 Form (sheet, strip, plate, bar, or wire),
- 5.1.4 Condition (See 6.3),
- 5.1.5 Mechanical properties (if applicable, for special conditions),
- 5.1.6 Finish (See 6.2),
- 5.1.7 Applicable dimensions including size, thickness, width, or drawing number,
- 5.1.8 Special tests, if any, and
- 5.1.9 Other requirements.

## 6. Materials and Manufacture

6.1 The various titanium mill products covered in this specification normally are formed with the conventional forging and rolling equipment found in primary ferrous and nonferrous plants. The alloy is usually multiple melted in arc furnaces (including furnaces such as plasma arc and electron beam) of a type conventionally used for reactive metals.

6.2 *Finish*—The mill product may be furnished to the implant manufacturer as mechanically descaled or pickled, sandblasted, chemically milled, ground, machined, peeled, polished, combinations of these operations, or as specified by the purchaser.

6.3 *Condition*—Material shall be furnished in the annealed or cold-worked condition.

## 7. Chemical Requirements

7.1 The heat analysis shall conform to the chemical composition of Table 1. Ingot analysis may be used for reporting all chemical requirements, except hydrogen. Samples for hydrogen shall be taken from the finished mill product. Supplier shall not ship material with chemistry outside the requirements specified in Table 1.

7.1.1 Requirements for the major and minor elemental constituents are listed in Table 1. Also listed are important residual elements. Analysis for elements not listed in Table 1 is not required to verify compliance with this specification.

7.2 *Product Analysis*—Product analysis tolerances do not broaden the specified heat analysis requirements but cover variations between laboratories in the measurement of chemical content. The supplier shall not ship material that is outside the limits specified in Table 1. The product analysis tolerances shall conform to the product tolerances in Table 2.

7.2.1 The product analysis is either for the purpose of verifying the composition of a heat or manufacturing lot or to determine variations in the composition within the heat.

**TABLE 1 Chemical Requirements**

Element	Composition, %
Nitrogen, max	0.05
Carbon, max	0.08
Hydrogen, max	0.012 <sup>A</sup>
Iron, max	0.25
Oxygen, max	0.13
Aluminum	5.5–6.50
Vanadium	3.5–4.5
Titanium <sup>B</sup>	balance

<sup>A</sup> Material 0.032 in. (0.813 mm) and under may have hydrogen content up to 0.0150 %.

<sup>B</sup> The percentage of titanium is determined by difference and need not be determined or certified.

**TABLE 2 Product Analysis Tolerance<sup>A</sup>**

Element	Tolerance Under the Minimum or Over the Maximum Limit (Composition %) <sup>B</sup>
Nitrogen	0.02
Carbon	0.02
Hydrogen	0.0020
Iron	0.10
Oxygen	0.02
Aluminum	0.40
Vanadium	0.15

<sup>A</sup> See AMS 2249.

<sup>B</sup> Under minimum limit not applicable for elements where only a minimum percentage is indicated.

7.2.2 Acceptance or rejection of a heat or manufacturing lot of material may be made by the purchaser on the basis of this product analysis.

7.2.3 For referee purposes, use Test Methods E 120, E 1409, and E 1447 or other analytical methods agreed upon between the purchaser and the supplier.

7.3 Ensure that the samples for chemical analysis are representative of the material being tested. The utmost care must be used in sampling titanium for chemical analysis because of its affinity for elements such as oxygen, nitrogen, and hydrogen. In cutting samples for analysis, therefore, the operation should be carried out insofar as possible in a dust-free atmosphere. Cutting tools should be clean and sharp. Samples for analysis should be stored in suitable containers.

## 8. Mechanical Requirements

8.1 The material supplied under this specification shall conform to the mechanical property requirements in Table 3.

8.2 Specimens for tension tests shall be machined and tested in accordance with Test Methods E 8. Tensile properties shall be determined using a strain rate of 0.003 to 0.007 in./in./min (mm/mm/min) through yield and then the crosshead speed may be increased so as to produce fracture in approximately one additional minute.

8.3 For sheet and strip, the bend test specimen shall withstand being bent cold through an angle of 105° without fracture in the outside surface of the bent portion. The bend shall be made around a mandrel which has a diameter equal to that shown in Table 3.

8.4 *Number of Tests:*

8.4.1 *Bar, Forging Bar, Shapes, and Wire*—Perform at least one tension test from each lot. Should any of these test specimens not meet the specified requirements, test two additional test pieces representative of the same lot, in the same manner, for each failed test specimen. The lot will be considered in compliance only if both additional test pieces meet the specified requirements.

8.4.2 *Sheet, Strip, and Plate*—Perform at least one tension and one bend test from each lot. Tension and bend property requirements apply in both the longitudinal and transverse directions. Tests in the transverse direction need be made only on product from which a specimen not less than 8.0 in. (200 mm) in length for sheet and 2.50 in. (64 mm) in length for plate can be taken. Should any of these test specimens not meet the specified requirements, test two additional test pieces representative of the same lot, in the same manner, for each failed test

**TABLE 3 Annealed Mechanical Properties<sup>A</sup>**

Nominal Diameter or Distance Between Parallel Sides, in. (mm)	Tensile Strength min, psi (MPa)	Yield Strength (0.2 % offset) min, psi (MPa)	Elongation <sup>B</sup> in 4D or 4W min, %			Reduction of Area <sup>C</sup> min, %		
			L —	LT —	ST —	L —	LT —	ST —
Under 0.187 (4.75) thickness or diameter	125 000 (860)	115 000 (795)	10	...	...	...	...	...
0.187 (4.75) to under 1.75 (44.45), incl	125 000 (860)	115 000 (795)	10	...	...	25	...	...
1.75 (44.45) to under 2.50 (63.50), incl	120 000 (825)	110 000 (760)	8	...	...	20	...	...
2.50 (63.50) to 4.00 (101.60), incl	120 000 (825)	110 000 (760)	8	8 <sup>D</sup>	8 <sup>D</sup>	15	15 <sup>D</sup>	15 <sup>D</sup>
	Bend Test <sup>E</sup>							
Under 0.070 (1.778) in thickness	9 T							
0.070 (1.778) to 0.187 (4.75), incl	10 T							

<sup>A</sup> Mechanical properties for conditions other than those listed in this table may be established by agreement between the supplier and the implant manufacturer.

<sup>B</sup> Elongation of material 0.062 in. (1.575 mm) or greater in diameter or thickness shall be measured using a gage length of 2 in. or 4 D or 4 W. The gage length must be reported with the test results. Elongation of material under 0.062 in. (1.575 mm) in diameter or thickness may be obtained by negotiation. L = longitudinal; LT = long transverse; ST = short transverse.

<sup>C</sup> Applies to bar, plate, and forgings only. L = longitudinal; LT = long transverse; ST = short transverse. For round bar the long and short transverse are identical tests, therefore only one transverse is required.

<sup>D</sup> Transverse requirements in Table 3 apply only to product from which a tensile specimen not less than 2.50 in. (63.5 mm) in length can be obtained.

<sup>E</sup> Bend test applicable to sheet and strip products; T = thickness of bend specimen in reference to diameter of bend.

specimen. The lot will be considered in compliance only if both additional test pieces meet the specified requirements.

## 9. Special Requirements

9.1 The microstructure shall be a fine dispersion of the alpha and beta phases resulting from processing in the alpha plus beta field. There shall be no continuous alpha network at prior beta grain boundaries. There shall be no coarse, elongated alpha platelets.

9.2 Determine the beta transus temperature for each heat by a suitable method and report on the material certification if required by the purchaser.

9.3 Alpha case is not permitted for products supplied with a machined, ground, or chemically milled surface finish. For other products, there will be no continuous layer of alpha case when examined at 100× magnification.

## 10. Certification

10.1 The supplier shall provide a certification that the material was tested in accordance with this specification. A report of the test results shall be furnished to the purchaser at the time of shipment.

## 11. Quality Program Requirements

11.1 The producer shall maintain a quality program as defined in ASQ C1.

## 12. Keywords

12.1 metals (for surgical implants); orthopaedic medical devices; titanium alloys; titanium alloys (for surgical implants)

## APPENDIXES

### (Nonmandatory Information)

#### X1. RATIONALE

X1.1 The purpose of this specification is to characterize the chemical, physical, mechanical, and metallurgical properties of wrought annealed titanium-6aluminum-4vanadium ELI (extra low interstitial) alloy to be used in the manufacture of surgical implants.

X1.2 The microstructural requirements contained in this

standard represent the current general consensus of opinion with respect to optimization of mechanical properties for implant applications.

X1.3 The minimum mechanical properties specified assure a baseline of strength and ductility for the highly stressed devices for which this alloy is typically used.

## **X2. BIOCOMPATIBILITY**

X2.1 The alloy composition covered by this specification has been employed successfully in human implant applications in contact with soft tissue and bone for over a decade. Due to the well-characterized level of biological response exhibited by this alloy, it has been used as a control material in Practice F 981.

X2.2 No known surgical implant material has ever been shown to be completely free from adverse reactions in the human body. Long-term clinical experience of the use of the material referred to in this specification, however, has shown that an acceptable level of biological response can be expected, if the material is used in appropriate applications.

## **SUMMARY OF CHANGES**

Committee F04 has identified the location of selected changes to this standard since the last issue (F 136 – 02) that may impact the use of this standard.

- (1) Section 3, Terminology, was added.
- (2) Section 8.4 was revised, and subsections 8.4.1 and 8.4.2 were added.

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or [service@astm.org](mailto:service@astm.org) (e-mail); or through the ASTM website ([www.astm.org](http://www.astm.org)).*